

TYPE:	A resin rich two-pack cold cured vinyl ester/ acrylic copolymer containing small quantities of wax.
SUGGESTED USE:	As a veil/top coat in aggressive chemical environments which would otherwise attack the glass present in Corroglass and Polyglass products.
LIMITATIONS:	Not designed for use as a stand-alone product. Where possible the product should not be overcoated with itself or other products due to the wax within the system. Recommendations regarding repair and overcoating are available from Corrocoat Technical Services.
HEALTH & SAFETY:	Before handling or using this product the material safety data sheet should be read and all precautions observed.
SURFACE PREPARATION:	Polyglass VE Veil Coat would normally be applied only over the surface of correctly applied Corroglass or Polyglass products.
APPLICATION EQUIPMENT:	Airless spray or hand application. Graco King 30:1 (or greater) or similar airless pump, 10mm diameter (3/8") nylon lines. Large bore type mastic gun with 20-30 thou reversible or titan adjustable tip.
MIXING RATIO:	98:2 base to hardener
HARDENER TYPE:	Corrocoat catalyst P2-45
POT LIFE:	Approximately 50 minutes at 20°C, will vary dependent upon temperature. Please refer to Polyglass Application Data sheet.
THINNERS:	Do not add any thinners to this product. Addition of styrene should only be carried out when specified by Corrocoat Technical Services.
PACKAGING:	20 Litre composite kits (including catalyst and inhibitor).

STORAGE LIFE:	6 Months at temperatures below 20°C and away from direct sunlight. Frequent temperature cycling will shorten storage life. See other information for extension of shelf life.
COLOUR AVAILABILITY:	Unpigmented or off white only.
RECOMMENDED DFT:	200-400 microns
THEORETICAL SPREADING RATE:	3.3m ² /litre at 300 microns
VOLUME SOLIDS:	This material contains volatile liquid convertible to solids. Volume solids obtained will vary dependent upon polymerisation conditions. Nominally 99.5% of the contents are convertible to solid.
PRACTICAL SPREADING RATE:	2.3m ² /litre at 300 microns dft Note: This information is given in good faith but may increase dependent upon environment conditions, the geometry and nature of work undertaken and the skill and care of application. Corrocoat accept no responsibility for any deviation from these values.
TEMPERATURE LIMITS:	110°C immersed. 165°C non-immersed. No known lower limit.
SPECIFIC GRAVITY:	1.07 gcm ⁻³ (mixed)
OVERCOATING:	Overcoating of this product is not recommended. Should this be required please consult Corrocoat Technical Services. Once the maximum overcoating time has been reached, the adhesion values attained by any subsequent coat will reduce dramatically. It is important to observe maximum overcoating times and note these will vary with climatic conditions. Any further application of coating at this juncture should be treated as a repair, with the surface flashed over to provide a physical key. Styrene cannot be used to reactivate the surface and may in some cases impair adhesion.
CLEANING SOLVENT:	Methyl Ethyl Ketone etc before gelation.

Reviewed: July 2011**Reviewed 02/2014 (no change)****Reviewed 12/2015****Reviewed 05/2016 (no change)****Corrocoat Limited, Forster Street, Leeds LS10 1PW. Tel: (0113) 276 0760. Fax: (0113) 2760700**